

# AL-T High-Performance Grease



## High-temperature grease | long-term lubrication

WEICON AL-T is suitable for rolling and sliding bearings, joints, levers, sliding guides, spindles, spline shafts, and at all sliding speeds permitted for grease lubrication. AL-T can be used in many industrial applications.

### Technical Data

Short description	KPL 2 R -20	
Consistency classification	DIN 51818	NLGI grade 2
Base	Aluminium-complex soap / mineral oil	
Density	(+20°C) DIN 51757	0,94 g/cm <sup>3</sup>
Four ball weld test property load	DIN 51350	2.200 N
Four ball weld test weld load	DIN 51350	2.400 N
Four ball weld test calotte value	DIN 51350 (1min/1000N)	2 mm
Rotation speed parameter	200.000	
Cone penetration	DIN ISO 2137	265 - 295 1/10 mm
Water resistance	DIN 51807	0 - 90
Heat capacity	DIN EN ISO 22007-4	1,49 J/(g·K)
Thermal conductivity	0,372 W/m·K	
Dielectric strength	DIN EN 60243-1 (20°C)	11,0 kV/mm
Dripping point	IP 396	> 210 °C
Kinematic viscosity (40 °C)	DIN 51 562	230 mm <sup>2</sup> /s
Kinematic viscosity (+100 °C)	DIN 51 562	15 mm <sup>2</sup> /s
EMCOR-corrosion test	DIN 51 802	0 / 0
Temperature conductivity	0,265 mm <sup>2</sup> /s	
Temperature resistance	-25°C to +190°C	
Shelf life	24 mon.	

### Approvals / Guidelines

ISSA Code	75.509.01
IMPA Code	450444   450445

### Surface pre-treatment

First clean the surface to be lubricated with WEICON Cleaner S, depending on the degree of soiling. If screws have already been used, process with the wire brush and clean with WEICON Cleaner S.

### Processing

Apply AL-T evenly.

### Storage

Store in tightly closed original container. Do not store with oxidising agents. Keep container tightly closed and store in a cool, well-ventilated area. Recommended storage temperature: Room temperature.

### Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

### Available sizes

- 10018579 AL-T High-Performance Grease, 0,4 kg
- 10018595 AL-T High-Performance Grease, 5 kg

### Conversion table

(°C x 1.8) + 32 = °F	Nm x 8.851 = lb·in
mm/25.4 = inch	Nm x 0.738 = lb·ft
µm/25.4 = mil	Nm x 141.62 = oz·in
N x 0.225 = lb	mPa·s = cP
N/mm <sup>2</sup> x 145 = psi	N/cm x 0.571 = lb/in
MPa x 145 = psi	kV/mm x 25.4 = V/mil

Note  
The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weicon.cz

WEICON GmbH & Co. KG  
(Headquarters) Germany  
phone +49 (0) 251 9322 0  
info@weicon.de

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
office@weicon.com

WEICON South East Asia Pte Ltd  
Singapore  
Phone (+65) 6710 7671  
info@weicon.com.sg

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es

WEICON Italia S.r.l.  
Italy  
phone +39 (0) 010 2924 871  
info@weicon.it

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Turkey  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr